



# ODOUR LESS

ALKYD/STYRENE ACRYLATE  
PRIMER-SEALER NO-4000

## Features

- Use on Smoke Damaged Walls
- Virtually Odourless
- Blocks most stains
- Quick Drying

## Recommended For

Seals stains on interior drywall, plaster or wood prior to repainting with either alkyd or latex paints in any level of sheen. Use to block out water or nicotine stains on acoustical tile. It is also an excellent choice for sealing soot and smoke stains on fire damaged walls. Due to its extremely low odour, it can be confidently used for maintenance work on occupied premises. This product can be used on exterior masonry surfaces and for spot priming on exterior wood, shingles and composition siding.

## General Description

Odour Less Primer is a virtually odourless, solvent based, quick drying sealer which is effective over a broad spectrum of stains including many which are difficult to seal with a water based stain suppressor. Odour Less Primer can be used over water, tannin, smoke, rust, pencil, ink, nicotine, coffee and most other stains. Any slight odour detected is milder than latex paint, inoffensive and dissipates in 15 minutes. Odour Less Primer can be used on bare or previously painted surfaces. It dries in 30 minutes and can be top-coated in two hours.

## Limitations

- Do not apply if the surface, material or ambient temperature is below 7.2 °C (45 °F).
- Do not use as a whole house paint primer on siding.
- Not recommended for use on PVC or CPVC plastics.

## Product Information

<b>Colours — Standard:</b> NO-4000, White	<b>Technical Data</b> <span style="float: right;"><b>White</b></span>																							
<b>— Tint Bases:</b> N/A Can tint up to 2 oz. Universal Colorant	<table border="1"> <tr> <td>Vehicle Type</td> <td>Alkyd/Styrene Acrylic</td> </tr> <tr> <td>Pigment Type</td> <td>Titanium Dioxide</td> </tr> <tr> <td>Volume Solids</td> <td>56.9 ± 1.0%</td> </tr> <tr> <td>Coverage per 3.79 L at Recommended Film Thickness</td> <td>30.2 – 39.5 sq. m. (325 – 425 sq. ft.)</td> </tr> <tr> <td>Recommended Film Thickness</td> <td>– Wet 3.8 – 5.0 mils – Dry 2.2 – 2.8 mils</td> </tr> </table>	Vehicle Type	Alkyd/Styrene Acrylic	Pigment Type	Titanium Dioxide	Volume Solids	56.9 ± 1.0%	Coverage per 3.79 L at Recommended Film Thickness	30.2 – 39.5 sq. m. (325 – 425 sq. ft.)	Recommended Film Thickness	– Wet 3.8 – 5.0 mils – Dry 2.2 – 2.8 mils													
Vehicle Type	Alkyd/Styrene Acrylic																							
Pigment Type	Titanium Dioxide																							
Volume Solids	56.9 ± 1.0%																							
Coverage per 3.79 L at Recommended Film Thickness	30.2 – 39.5 sq. m. (325 – 425 sq. ft.)																							
Recommended Film Thickness	– Wet 3.8 – 5.0 mils – Dry 2.2 – 2.8 mils																							
<b>— Special Colours:</b> Contact your dealer.	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.																							
<b>Certification:</b>  The product supported by this data sheet contains a maximum of 350 grams per litre VOC / VOS (2.92 lbs/gal.) excluding water and exempt solvents. This product is compliant as a Specialty Primer/Sealer/Undercoater. This product is currently approved under MPI # 39, # 45 and # 136.	<table border="1"> <tr> <td>Dry Time @ 25 °C (77 °F) @ 50% RH</td> <td>– Tack Free 30 Minutes – To Recoat 2 Hours – To Cure 7 to 10 Days</td> </tr> </table>	Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free 30 Minutes – To Recoat 2 Hours – To Cure 7 to 10 Days																					
Dry Time @ 25 °C (77 °F) @ 50% RH	– Tack Free 30 Minutes – To Recoat 2 Hours – To Cure 7 to 10 Days																							
<b>Technical Assistance:</b> Available through your local authorized Insl-x dealer. For the location of the dealer nearest you, call 1-800-225-5554 or visit <a href="http://www.Insl-x.ca">www.Insl-x.ca</a>	<table border="1"> <tr> <td>High humidity and cool temperatures will result in longer dry, recoat and service times.</td> </tr> <tr> <td>Dries By</td> <td>Oxidation</td> </tr> <tr> <td>Viscosity</td> <td>85 – 90 KU</td> </tr> <tr> <td>Flash Point</td> <td>39.4 °C (103 °F) or greater (TT-P-141, Method 4293)</td> </tr> <tr> <td>Gloss / Sheen</td> <td>Flat</td> </tr> <tr> <td>Surface Temperature at Application</td> <td>– Min. 7.2 °C (45 °F) – Max. 32.2 °C (90 °F)</td> </tr> <tr> <td>Thin With</td> <td>Do Not Thin</td> </tr> <tr> <td>Clean Up Thinner</td> <td>Mineral Spirits</td> </tr> <tr> <td>Weight Per 3.79 L</td> <td>6 kg (13.3 lbs)</td> </tr> <tr> <td>Storage Temperature</td> <td>– Min. 7.2 °C (45 °F) – Max. 35 °C (95 °F)</td> </tr> <tr> <td colspan="2" style="text-align: center;"><b>Volatile Organic Compounds (VOC)</b></td> </tr> <tr> <td>343 Grams/Litre</td> <td>2.86 Lbs./Gallon</td> </tr> </table>	High humidity and cool temperatures will result in longer dry, recoat and service times.	Dries By	Oxidation	Viscosity	85 – 90 KU	Flash Point	39.4 °C (103 °F) or greater (TT-P-141, Method 4293)	Gloss / Sheen	Flat	Surface Temperature at Application	– Min. 7.2 °C (45 °F) – Max. 32.2 °C (90 °F)	Thin With	Do Not Thin	Clean Up Thinner	Mineral Spirits	Weight Per 3.79 L	6 kg (13.3 lbs)	Storage Temperature	– Min. 7.2 °C (45 °F) – Max. 35 °C (95 °F)	<b>Volatile Organic Compounds (VOC)</b>		343 Grams/Litre	2.86 Lbs./Gallon
High humidity and cool temperatures will result in longer dry, recoat and service times.																								
Dries By	Oxidation																							
Viscosity	85 – 90 KU																							
Flash Point	39.4 °C (103 °F) or greater (TT-P-141, Method 4293)																							
Gloss / Sheen	Flat																							
Surface Temperature at Application	– Min. 7.2 °C (45 °F) – Max. 32.2 °C (90 °F)																							
Thin With	Do Not Thin																							
Clean Up Thinner	Mineral Spirits																							
Weight Per 3.79 L	6 kg (13.3 lbs)																							
Storage Temperature	– Min. 7.2 °C (45 °F) – Max. 35 °C (95 °F)																							
<b>Volatile Organic Compounds (VOC)</b>																								
343 Grams/Litre	2.86 Lbs./Gallon																							

◇ Reported values are for White. Contact dealer for values of other bases or colours.

## Surface Preparation

The surface to be painted must be clean, dry and free of dirt, wax, grease, rust, mildew, loose and peeling paint and all other contamination. Dirt, wax and chalk should be removed using a detergent solution. Scrub stained area vigorously to remove as much of the stain as possible. Mildew should be removed by washing with a solution of one part household bleach\* and three parts water. Rinse well and allow it to dry. Grease and oil should be removed using an Oil and Grease Emulsifier. Loose or peeling paint should be scraped or sanded and any remaining tightly adhering paint should be sanded to a featheredge. Remove sanding dust with a tack rag. Loose wallpaper and any residual paste should be removed by scraping, sanding or using a commercial wallpaper remover.

\*Follow bleach manufacturer's instructions for safe handling and use of bleach solution.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ [http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked\\_questions-questions\\_posees-eng.php](http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked_questions-questions_posees-eng.php)

## Application

Stir product thoroughly before application. Odour Less Primer can be applied by brush, roller, pad or spray. When applying by roller, let the texture of the surface determine the depth of nap. When brushing, use either a natural bristle brush or one with a nylon/polyester filament recommended for use with solvent based products. If applying by airless sprayer use a tip size .013 - .015. Do not apply Odour Less Primer unless the surface, material and ambient temperatures are 7.2 °C (45 °F) or over. Do not paint if surface temperature is within 5 degrees of the dew point.

**NOTE:** For best results, apply finish coat within 48 hours.

## Clean Up

Clean tools with mineral spirits immediately after use. Clean spills quickly with mineral spirits. Dried material is difficult to remove.

## Environmental Health & Safety Information

### CAUTION

READ INSTRUCTIONS BEFORE USING

DANGER OF COMBUSTION

Keep away from flames or sparks.

Materials such as rags used with this product may begin to burn by themselves.

After use, put rags in water or lay flat to dry, then discard.

**Use only in a well ventilated area.** Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN**

**Refer to Safety Data Sheet for additional health and safety information.**